



Article Cold Spray Deposition of MoS₂- and WS₂-Based Solid Lubricant Coatings

Jeffrey R. Lince ^{1,*}, Peter Woods ², Eric Woods ², Wai H. Mak ³, Scott D. Sitzman ³ and Andrew J. Clough ³

- ² Applied Tungstenite, Inc., Minden, NV 89423, USA; petewoods@appliedtungstenite.com (P.W.); ericwoods@appliedtungstenite.com (E.W.)
- ³ The Aerospace Corporation, El Segundo, CA 90245, USA; wai.h.mak@aero.org (W.H.M.); scott.d.sitzman@aero.org (S.D.S.); andrew.j.clough@aero.org (A.J.C.)
- Correspondence: jeff@spacetribology.com

Abstract: The cold spray deposition technique has been used to produce a new class of solid lubricant coatings using powder feedstocks of the metal disulfides WS₂ or MoS₂, either pure or mixed with Cu and Ni metal powders. Friction and cycle lives were obtained using ball-on-flat reciprocating tribometry of coated 304 SS flats in dry nitrogen and vacuum at higher Hertzian contact stresses (S_{max} = 1386 MPa (201 ksi)). The measured friction and thickness of the coatings were much lower than for previous studies (COF = 0.03 ± 0.01 and $\leq 1 \mu$ m, respectively), which is due to their high metal disulfide:metal ratios. Cu-containing metal sulfide coatings exhibited somewhat higher cycle lifetimes than the pure metal sulfide coatings, even though the Cu content was only ~1 wt%. Profiling of wear tracks for coatings tested to 3000 cycles (i.e., pre-failure) yielded specific wear rates in the range $3-7 \times 10^{-6}$ mm³N⁻¹m⁻¹, similar to other solid lubricant coatings. When compared to other coating techniques, the cold spray method represents a niche that has heretofore been vacant. In particular, it will be useful in many precision ball-bearing applications that require higher throughput and lower costs than sputter-deposited MoS₂-based coatings.

Keywords: solid lubrication; anti-wear coatings; dry-film lubricants; cold spray; spacecraft; tribology; molybdenum disulfide; tungsten disulfide; ball bearings

1. Introduction

Solid lubricant coatings used on spacecraft are available in a number of different formulations and are produced by methods including mixing with organic and inorganic binders, air impingement, and sputter deposition [1]. There is no panacea: each type of coating has strengths and weaknesses, among attributes such as coefficient of friction (COF), endurance, adhesion, thickness, load-carrying capability, type of coated device, and cost. For example, both sputter-deposited and air-impinged MoS₂-based coatings exhibit very low friction and are thin enough to be used in tolerance-sensitive ball-bearing applications, but sputter-deposited coatings are somewhat expensive, while air-impinged coatings have much lower endurance. Bonded MoS₂ coatings exhibit low friction and significant endurance, but the thickness may be too high and load-carrying capability too low for many applications.

Cold spray is a newer technique among thermal spray coatings that is often used for depositing relatively thick, dense metal coatings [2]. It can be performed rapidly, inexpensively, with relatively little surface preparation, and can even be carried out in the field using portable units. Unlike other flame and plasma spray coatings, cold spray uses lower temperatures (typically 0–1100 °C), higher impingement speeds (typically 300–1200 m/s), and inert gases, such as nitrogen and helium, as propellant gases. These attributes protect substrate properties and enable better control over the coating composition because the temperatures are generally below the particles' melting temperatures [3]. However, methods to improve the tribological



Citation: Lince, J.R.; Woods, P.; Woods, E.; Mak, W.H.; Sitzman, S.D.; Clough, A.J. Cold Spray Deposition of MoS₂- and WS₂-Based Solid Lubricant Coatings. *Lubricants* **2024**, *12*, 237. https://doi.org/10.3390/ lubricants12070237

Received: 10 May 2024 Revised: 3 June 2024 Accepted: 11 June 2024 Published: 28 June 2024



Copyright: © 2024 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/).

¹ Space Tribology Consulting, Culver City, CA 90232, USA

(friction and wear) properties of these coatings are in their infancy. Cold spray may be especially attractive for solid lubricants, such as MoS₂, since they can decompose at elevated temperatures and in oxidizing environments.

Several groups have investigated the deposition of solid lubricating coatings via cold spray [4–10]. Metal/solid lubricant composite coatings based on Cu/MoS₂ exhibited optimum tribological performance for low MoS₂ contents (i.e., ≤ 5 wt% in the initial powder feedstock) [4,7–9]. In studies by Zhang et al., 5 wt% MoS₂ in the initial powder mixture resulted in 1–3 wt% in the coating [7]. A separate study by Zhang using separate feeders for Cu and MoS₂ resulted in similar MoS₂ contents in the coating [9]. Resultant ball-on-flat tribological testing of Cu/MoS₂ in dry air showed a COF of 0.14, a considerable drop from that for pure Cu (i.e., 0.7) [7]. Testing of Cu/MoS₂ in nitrogen (N₂) showed a COF of 0.38, and Cu/MoS₂-WC showed a COF of 0.27, compared to 0.5 for pure Cu [9].

More recently, a study was conducted by Dey et al. on cold spray deposition of Inconel/WS₂ coatings, augmented by a laser-assisted process [11]. Nominal WS₂ content (in the initial powder mixture) was 15 wt%. Ball-on-flat tribological testing of the coatings showed a COF of 0.11, considerably lower than that for Inconel (i.e., 0.51).

In the present study, we studied metal/solid lubricant composite coatings produced by cold spray based on either Cu or Ni mixed with MoS₂ or WS₂. Pure MoS₂ or WS₂ coatings were also studied. In contrast to earlier studies, our coatings exhibited much lower COF values of 0.03 ± 0.01 . They were also much thinner than previous coatings ($\leq 1 \mu m$ compared to >100 μm), which is optimum for precision spacecraft applications, such as ball bearings. Differences in friction and the coating thickness were due in part to high solid lubricant contents (>95 wt% measured in our optimized coatings, compared to $\leq 5 wt\%$ in the previously studied coatings).

2. Materials and Methods

Most substrates used for coatings were made of polished 304 stainless steel because of the importance of this and similar steels in space mechanisms; other materials were briefly explored, including Al6061, Ti6Al4V, and other stainless steels. All 304 SS substrates used for the final grade coatings were polished to a finish of $R_a = 20 \mu m$. Substrates were tested with and without 5-micron alumina grit blasting and were ultrasonically cleaned in acetone prior to coating. Cold spray coatings for pathfinding measurements were obtained from ASB Industries using their Impact Innovations Cold Gas Spray System. Later coatings were produced at Applied Tungstenite using Kinetic Metallization (KM) cold spray equipment purchased from Inovati. The KM equipment was fitted with a particle fluidizer that uses a rotating brush to sweep feedstock powder through holes in a sieve plate, breaking up agglomerated particles and controlling the powder feed rate into the carrier gas [12]. This promoted coating uniformity and minimized sample-to-sample variation. Optimum feed rates were generally low, in the 20–30% range (100% refers to the highest feed rate speed and does not correlate with actual mass feed rates). Optimum carrier gas temperatures were in the range 400-500 m/s.

Several types and sizes of powder particle sizes were used. The Cu particle size range was +11/-38 µm and WS₂ average particle size was 5 µm. The Cu particle size ranges evaluated were +0.93/-2.81 µm and +11/-38 µm, with an average diameter of 100 nm. Ni particle sizes were +11/-45 µm, with average diameters of 1 and 5 µm. Average particle widths of WS₂ were 100 nm and 24 µm. The average particle width of MoS₂ was 15 µm. Purities of all powders were ≥99.5%.

Several hundred samples were produced over the course of this project, the majority of which were evaluated tribometrically. Friction measurements were primarily obtained with an Anton Paar TRB³ ball-on-flat tribometer, fitted for conducting reciprocating linear measurements. Testing was conducted as per ASTM G133, with minor differences. The 100Cr6 6 mm-diameter steel balls were used as the counter-faces and were cleaned using IPA prior to testing. They were held stationary and loaded using either a 2N or 10N dead weight load onto a metal flat, onto which a cold spray coating was deposited. The nominal

maximum Hertzian contact stress (S_{max}) varied based on the coating substrate material. For a 100Cr6 ball and 304 SS flat material, S_{max} was 811 MPa (118 ksi) and 1386 MPa (201 ksi), for 2N and 10N loads, respectively. The track length was 10 mm, and the sliding speed was 5.65 cm/s. Each data point shown in friction scans was averaged from a forward and reverse scan in the middle 6 mm of the track to avoid track edge effects. The failure criterion was COF > 0.5.

Tests using the TRB³ were conducted in flowing dry nitrogen (N₂) to remove moisture and oxygen from the testing environment. This approach is often used to model the spacecraft environment, since humidity has a major effect on the performance of MoS₂ and WS₂ solid lubricants. There are small differences seen in the behavior of these materials between dry N₂ and vacuum environments, but this approach is often used because of the difficulty of testing in a vacuum. The tribometer enclosure was purged with N₂ until the humidity was measured as $0 \pm 2\%$ RH. Even if the actual value was at the top of this uncertainty range, i.e., 2% RH, negligeable effects would be expected: a study of sputtered MoS₂ coatings showed that there was no detectable difference in coating endurance over the humidity range of 0.02 to 2.0% RH (higher humidities did result in lower endurance) [13].

Additional ball-on-flat tribometer measurements were obtained at the Aerospace Corporation using an RTEC MVT-2 Vacuum Tribometer operating in the linear reciprocating mode at a vacuum level of 0.047 Pa (3.5×10^{-4} Torr). Other conditions were set to be close to those for the previous 10N normal load testing on the TRB³ tribometer, achieving a match to the 201 ksi S_{max} value within 0.5%. The sliding speed was 3 cm/s.

Cross-sections of some of the coatings were obtained using focused ion beam (FIB) techniques at the Aerospace Corporation. The resultant cross-sections could then be analyzed using scanning electron microscopy equipped with energy-dispersive X-ray analysis (SEM/EDX). These provided the thickness, morphology, and composition of the coatings.

X-ray photoelectron spectroscopy (XPS) of some of the coatings was conducted using a Physical Electronics Versaprobe II instrument. Spectral binding energies were calibrated by assigning the adventitious carbon C 1s peak to a binding energy of 284.8 eV.

An EDAX Ametek Orbis PC Micro-XRF X-ray Fluorescence (XRF) Spectrometry instrument was used in conjunction with SEM/EDX measurements to better quantify the coating composition.

To evaluate average wear rates, some coatings were tested using the TRB³, stopping after 3000 cycles (i.e., prior to failure). Estimates of wear depths and volumes were obtained using a Zygo Zegage Plus configured for White Light Interferometry (WLI) imaging, an optical profilometry technique that enables development of a 3D image of a sample surface (conducted at Covalent Metrology). It has a lateral resolution of 2.5 μ m and vertical resolution of ~1 nm. The instrument also enabled measurement of the surface roughness of the as-deposited coatings.

Optical images of some of the balls after 3000-cycle testing were obtained using a Dino-Lite Digital Microscope (Model AM7915MZTL).

3. Results

3.1. Tribology

Pathfinding cold spray coatings were grown at ASB Industries. Other early coatings were produced using KM equipment at Applied Tungstenite. With the goal of reproducing results by other researchers, composite coatings with high metal:sulfide ratios in the powder feedstock were studied during this early period. However, XRF showed that the coatings exhibited lower metal:sulfide ratios than those obtained in previous studies [4,7–9]. For example, Cu/WS₂ coatings nominally containing 8 wt% WS₂ grown at ASB, and coatings grown with nominally 5 wt% WS₂ using KM equipment, were shown to contain actual Cu contents of 37 and 23 wt%, respectively (compared to, for example, results from [7], which showed that Cu/MoS₂ samples with nominally 5 wt% MoS₂ were measured to contain 1–3 wt% MoS₂). Note that for clarity, the coatings in this study were identified by their

nominal composition; that is, the composition of the powder mixture as it was added to the powder feeder. Measurements by XRF were also conducted of the actual composition of some of the coatings, and these will be discussed periodically in the text.

Ball-on-flat tribometry results for two such coatings deposited on 304 SS are shown in Figure 1 (obtained using a 2N normal load and a N₂ atmosphere). The coatings showed significant friction reduction of COF~0.15–0.25, compared to that obtained for a pure cold spray Cu coating of 0.6. In addition, the coatings lasted until the end of the 1000-cycle test without failure. The performance was similar to that of previously studied Cu/MoS₂ coatings that showed a COF of 0.14 for a test with the same cycle length [7]. This similarity is in spite of the differences in sulfide contents (63 and 77 wt% WS₂ compared with 1–3 wt% MoS₂).



Figure 1. Tribometry results from the 1000-cycle tests using a 2N load on Cu/WS₂ cold spray coatings on 304 SS substrates. Testing was conducted in dry N₂. Shown are coatings produced on ASB equipment (blue; nominally 8 wt% WS₂) and Applied Tungstenite equipment (orange; nominally 5 wt% WS₂). Cu particle size range was $+11/-38 \mu m$ and WS₂ average particle size was 5 μm . X-ray fluorescence spectrometry (XRF) measurements of the KM coatings showed the actual WS₂ contents were 63 and 77 wt% for the ASB and KM coatings, respectively.

Similar results were obtained when coatings with the same nominal composition were deposited on Ti6Al4V alloy (see Figure 2).

Coatings were also studied using WS_2 with Ni metal. Tribometer results for Ni/WS₂ cold spray coatings grown using ASB and KM equipment, and both nominally containing 8 wt% WS₂, are shown in Figure 3. Although the friction started low in both cases, the coatings failed relatively quickly, with the ASB coating failing after a few cycles, and the KM coating COF slowly rising, followed by failure at 120 cycles.



Figure 2. Tribometry results from the 1000-cycle tests using a 2N load on Cu/WS₂ cold spray coatings on Ti-6Al-4V substrates. Testing was conducted in dry N₂. Shown are coatings produced on ASB equipment (blue; nominally 8 wt% WS₂) and Applied Tungstenite equipment (orange; nominally 5 wt% WS₂). Cu particle size range was $+11/-38 \mu m$ and WS₂ average particle size was 5 μm . The XRF measurement of the KM coating showed the actual WS₂ content was 81 wt%.



Figure 3. Tribometry results from the 1000-cycle tests using a 2N load on Ni/WS₂ cold spray coatings on Ti-6Al-4V substrates. Testing was conducted in dry N₂. Shown are coatings produced on ASB equipment (blue; nominally 8 wt% WS₂) and Applied Tungstenite equipment (orange; nominally 8 wt% WS₂). Ni particle size range was $+11/-45 \mu m$ and WS₂ average particle size was $5 \mu m$. The XRF measurement of the KM coating showed the actual WS₂ content was 59 wt%.

Subsequent to this initial pathfinding period, coatings were all produced using KM equipment at Applied Tungstenite. During the process of obtaining optimized coatings, a number of coating parameters were varied, including the nominal metal:sulfide ratio in the powder feedstock, particle size (of both metal and sulfides), feed gas temperature and pressure, powder feed rate, and substrate material. Although all these affected the tribology

and composition of the coatings, the nominal metal:sulfide ratio (i.e., the composition of the powder feedstock) emerged as the critical parameter. In particular, low added metal contents were found to yield the best friction and endurance results. This is illustrated in Figure 4, where tribometry results for a number of Cu/WS₂ coatings with different initial Cu:WS₂ ratios are shown (at a 2N normal load; the coating with nominally 5 wt% WS₂ is also represented in Figure 1). Increasing nominal WS₂ content from 5 wt% to 8 wt% resulted in a significant drop in COF, although endurance did not improve, with the 8 wt% coating failing at 700–800 cycles. The coating with 20 wt% WS₂ content to 90 wt% resulted in an additional drop in COF, with the steady-state friction lasting throughout the 1000-cycle test.



Figure 4. Tribometry results from the 1000-cycle tests using a 2N load on Cu/WS₂ cold spray coatings on 304 SS substrates (deposited at Applied Tungstenite, as were all subsequent coatings in this study). Testing was conducted in dry N₂. Shown are coatings produced with nominal contents of 5 wt% WS₂ (blue), 8 wt% WS₂ (orange), 20 wt% WS₂ (green), and 90 wt% WS₂ (red). For the first three, the Cu particle size range was $\pm 11/-38 \mu m$ and WS₂ average particle size was 5 μm . For the 90 wt% WS₂ coating, the average Cu and WS₂ sizes were 1 μm and 24 μm , respectively (as discussed below, a similar performance was obtained for lower WS₂ sizes). Actual WS₂ contents measured by XRF for these coatings were 77.1, 97.6, 98.7, and 99.1 wt%, respectively (the coating with 5 wt% WS₂ is also shown in Figure 1).

Actual WS₂ contents were measured by XRF for these coatings: coatings with nominal concentrations of 5, 8, 20, and 90 wt% actually contained 77.1, 97.6, 98.7, and 99.1 wt% WS₂. Based on these results, it was not surprising that pure WS₂ coatings (i.e., with no added Cu) also demonstrated excellent performance, exhibiting low COF and lasting for an entire 5000-cycle test without failure (see the blue curve in Figure 5).

At this point in the investigation, many samples lasted for 5000+ cycles without failure. To better discriminate between the performance of different coatings, further investigation required altering tribometry testing parameters to encourage chances for failure in a reasonable timeframe, in particular by increasing the normal load from 2N to 10N. The concomitant increase in nominal maximum Hertzian contact stress (S_{max}) from 811 MPa (118 ksi) to 1386 MPa (201 ksi) is shown in Figure 5 for a pure WS₂ coating: the higher load result is shown in the orange curve to result in a failure at 2200 cycles.



Figure 5. Tribometry results from the 5000-cycle tests on a pure WS₂ cold spray coating on a 303SS substrate. Testing was conducted in dry N₂. Shown is data for testing with 2N (blue) and 10N (orange) normal load. The average WS₂ particle size was 24 μ m. The 2N test lasted the full 5000 cycles, while the 10N test failed after 2200 cycles.

The increase in load also resulted in the COF of the pure WS₂ coating dropping from ~0.022 to ~0.015. Like MoS_2 , WS₂ conforms to the Hertzian Contact Model [14], where the COF decreases as the normal load is increased. Specifically, the COF for such species is inversely proportional to the Hertzian contact stress, unlike solids that follow Amontons' Law, where the COF is independent of load [15]. This behavior is caused by the low shear strength of metal disulfides, as opposed to harder materials where the COF is related to surface interaction.

While the nominal composition of the feedstock powder had the most significant effect on performance, particle size had a modest effect on performance. This is partly because smaller metal particles exhibited less clogging in the KM cold spray machine. In particular, WS₂ showed the best performance when particles had a 100 nm average width. With MoS₂, good performance was obtained with average widths of 15 μ m (smaller MoS₂ sizes were briefly investigated and showed promising performance).

Optimized versions of six coating types were developed and are shown in Figures 6–11. Specifically, coatings with the following nominal compositions are shown: 1 μ m Cu + 90 wt% 100 nm WS₂, 1 μ m Cu + 90 wt% 15 μ m MoS₂, 1 μ m Ni + 88wt% 100 nm WS₂, 1 μ m Ni + 80 wt% 15 μ m MoS₂, 100 nm WS₂, and 15 μ m MoS₂.



Figure 6. Tribometry results on a Cu/WS₂ cold spray coating (with nominal WS₂ content of 90 wt%) on a 304 SS substrate. Testing was conducted in dry N₂. A 10N normal load was used and the test was run until failure. The average Cu particle size range was 1 μ m and the average WS₂ particle size was 100 nm. The larger spread of data for this scan is likely an equipment artifact and not representative of this sample.



Figure 7. Tribometry results on a Cu/MoS₂ cold spray coating (with nominal MoS₂ content of 90 wt%) on a 304 SS substrate. Testing was conducted in dry N₂. A 10N normal load was used and the test was run until failure. The average Cu particle size range was 1 μ m and the average MoS₂ particle size was 15 μ m.



Figure 8. Tribometry results on a Ni/WS₂ cold spray coating (with nominal WS₂ content of 88 wt%) on a 304 SS substrate. Testing was conducted in dry N₂. A 10N normal load was used and the test was run until failure. The average Ni particle size range was 1 μ m and the average WS₂ particle size was 100 nm.



Figure 9. Tribometry results on a Ni/MoS₂ cold spray coating (with nominal MoS₂ content of 80 wt%) on a 304 SS substrate. Testing was conducted in dry N₂. A 10N normal load was used and the test was run until failure. The average Ni particle size range was 5 μ m and the average MoS₂ particle size was 15 μ m.



Figure 10. Tribometry results on a pure WS_2 cold spray coating on a 304 SS substrate. Testing was conducted in dry N_2 . A 10N normal load was used and the test was run until failure. The average WS_2 particle size was 100 nm.



Figure 11. Tribometry results on a pure MoS_2 cold spray coating on a 304 SS substrate. Testing was conducted in dry N_2 . A 10N normal load was used and the test was run until failure. The average MoS_2 particle size was 15 μ m.

Average performance based on cycle life and steady-state COF for each coating type is summarized in Figure 12. All coatings exhibited average values in the range 0.02-0.03. The cycle life appeared somewhat better for the coatings using Cu or Ni additions than for the pure WS₂ and MoS₂ coatings, but definitive discrimination was difficult due to the magnitude of the data scatter. In any case, the data represent coatings that are competitive



with other dry-film lubricant formulations, with low friction and significant endurance at a high S_{max} value of 1386 MPa (201 ksi).

Figure 12. Summary of friction and endurance results for optimized cold spray solid lubricant coatings tested in dry N_2 with a 10N normal load on the Anton Paar TRB³ tribometer. Results are based on samples of the same types shown in Figures 6–11. Each data point represents 5 to 13 samples. Coating types show nominal composition, i.e., that represented in the initial powder mixture. Actual coating composition differed significantly, as discussed in the text.

To determine the amount of coating wear for each optimized coating formulation, we conducted tests with the Anton Paar tribometer at a fixed duration of 3000 cycles, which was prior to coating failure for all samples. This ensured that the wear calculations were for the coating only, and not for the underlying substrate, the latter of which would have been included if we ran the tests to failure.

For each of these 3000 tests, profilometry of the wear tracks was obtained using WLI imaging. For each wear track, three scans were obtained at different locations across the wear track. For each, the difference between the depth of the scan in the wear track and the average height of the neighboring unworn areas was determined. The three resulting values were averaged to yield an average wear depth in the wear track. Wear widths were also measured, which averaged ~ $0.14 \pm 0.2 \mu m$ for all samples.

Surface roughness values S_a and S_z were also calculated, both inside and outside the wear track. S_a is the standard arithmetic roughness averaged over the area of interest, while S_z is the average of the five largest peaks and valleys. S_z is useful because it provides a sense of the degree of large asperities in the contact region, which can be even more important than S_a in tribological contacts.

Results from the WLI imaging of one of the samples are shown in Figure 13. The blue line in the upper image represents the wear track, where the blue color represents a negative height due to wear, and these are the valleys seen in the three cross-sectional profile traces in the lower part of the figure. The green area is the level of the unworn

-0.2 -0.3 -0.4 -0.5 -0.6 -0.7

50

100

150

200

250

300

350

μm

400

450

coating, which was set arbitrarily to zero. The red areas next to the wear track represent positive heights and correspond to the raised "wings" in the profile traces in the lower part of the figure. These wings are likely worn coating material that has built up at the edges of the wear track. This material can act as a lubricant reservoir that can be cycled back into the contact region during sliding.



Figure 13. Raw data are shown from the White Light Interferometry (WLI) Imaging for a 1 μ m Cu/90% 100 nm WS₂ coating tested for 3000 cycles (i.e., pre-failure). A false-color image (**upper**) is shown, where the colors represent height, with red the highest, green the level of the unworn coating, and blue within the wear track. Three lines are shown across the wear track where profile traces were obtained. The three traces are shown overlayed (**lower**). The areas outside the wear track are set to zero height, and the wear depth can be determined from the minimum of the curve.

500

550

600

650

700

Roughness and wear results for the samples analyzed by WLI imaging are shown in Table 1. The S_a values were very small in the unworn areas outside the wear track. In contrast, the S_z values were large outside the wear track. These values describe an unworn coating that is very smooth on average but has a few large asperities. S_z was larger for the coatings that contained MoS₂, which is consistent with the larger particle size used in the feedstock. Although the coatings were enhanced in the smaller particle sizes, the larger MoS₂ size distribution resulted in the presence of a few large particles remaining.

Sample -	Roughness Inside Wear Track		Roughness Outside Wear Track		Average Wear Doubth (± 0.04)	Average Wear Rate
	S _a	S_z	S _a	S_z	- Deptil (±0.04)	$(\pm 0.4 \times 10^{-6})$
	μm	μm	μm	μm	μm	$\mathrm{mm^{3}N^{-1}m^{-1}}$
1 μm Cu 90% 15 μm MoS ₂	0.55	0.73	0.11	18.3	0.72	$7.2 imes 10^{-6}$
5 μm Ni 80% 15 μm MoS ₂	0.46	6.19	0.042	33.8	0.54	$5.0 imes 10^{-6}$
15 μm MoS ₂	0.38	0.83	0.086	84.7	0.45	$4.5 imes10^{-6}$
15 μm MoS ₂ (#2)	0.22	5.59	0.24	84.9	0.28	$3.1 imes10^{-6}$
100 nm WS ₂	0.43	0.41	0.028	5.50	0.47	$4.1 imes10^{-6}$
100 nm WS ₂ (#2)	0.48	0.58	0.029	12.1	0.50	$4.4 imes10^{-6}$
1 μm Cu 90% 100 nm WS ₂	0.54	1.93	0.13	9.4	0.60	$5.6 imes 10^{-6}$
1 μm Cu 90% 100 nm WS ₂ (#2)	0.45	-2.78	0.046	15.3	0.52	$4.5 imes 10^{-6}$
1 μm Ni 88% 100 nm WS ₂	0.46	1.05	0.027	5.09	0.57	$5.3 imes10^{-6}$

Table 1. Wear depth and surface roughness results on wear scars obtained using White Light Interferometry (WLI) imaging. Data in this table represent tests limited to 3000 cycles (i.e., pre-failure).

Inside the wear track, the S_a values increased slightly but were still relatively small. In contrast, the S_z values were significantly reduced after wear. The decrease in the S_z values may be explained by burnishing of the few larger lubricant particles during the run-in period. There appeared to be a small average increase in S_a after testing, although it decreased for a few samples. The variation is likely not statistically significant.

In general, the variation of S_a and S_z values for the samples may partially explain the large variation in cycle life seen in Figure 12.

Average wear rates can be determined from the wear depth results. Assuming that the cross-section of each wear track is a circular arc, the cross-sectional area can be estimated, which can be used to find the specific wear rate in units of $mm^3 N^{-1} m^{-1}$ [16,17]. The results are shown in the last column of Table 1. The assumption of a circular cross-section is supported by the lack of apparent wear of the spherical ball surface, as discussed below. In addition, a circular model provided a good fit to the wear track cross-section data.

The specific wear rates were all in the 10^{-6} range, which is much smaller than those for non-lubricating materials, such as metals and ceramics, and is typical for solid lubricant coatings [18]. Differences between wear rates of various coatings were relatively small and did not correlate with coating composition.

The contact regions of some of the balls used in the 3000-cycle tests were examined by optical microscopy, since changes in surface quality due to wear would be readily apparent on the surfaces of the highly polished balls. The surfaces appeared shiny, with some additional material that was likely a thin transfer film. No evidence of abrasive or adhesive wear was seen, which would have been observed as a non-reflective surface with multiple parallel lines or a distinctive galling pattern, respectively [19]. A microscope image of the ball used in one of the tests of the 1 μ m Cu/90% 100 nm WS₂ is shown on the left side of Figure 14. The contact region appeared as one would expect from a solid lubricant ball-on-flat test. There was no apparent wear in the center of the contact region (the darker elliptical area). The material surrounding the center of the contact region is likely transfer material from wear of the coating (the third body, as discussed above). A microscope image of the ball used in the 100 nm WS₂ 3000-cycle test is shown on the right side of Figure 14. Again, there was no apparent wear in the center of the contact region, and transfer material from wear of the coating surrounded this region. Further analysis using optical profiling techniques, such as WLI, could have provided a more quantitative measure of the presence or absence of wear but was not conducted in this study.





Figure 14. Optical images of ball counter-faces from a 3000-cycle test of a 1 μ m Cu/90% 100 nm WS₂ coating (**left**) and a 100 nm WS₂ coating (**right**). The ball contact region is shown with a blue arrow. The orange and white features are lighting artifacts. WS₂ contents refer to nominal composition based on the initial powder feedstock.

To demonstrate the performance of the coatings in a more space-like environment, ball-onflat tribometry was conducted on several coating formulations in a vacuum (3.5×10^{-4} Torr or 0.047 Pa) using an RTEC Vacuum Linear Reciprocating Tribometer. Vacuum testing was designed so that the loads and contact geometry (especially S_{max}) were close to those used in the N₂ testing in the Anton Paar tribometer. Typical vacuum tribometry data are shown in Figure 15 for a pure WS₂ cold spray coating on a 304 SS substrate.



Figure 15. Tribometry results on a pure WS₂ cold spray coating on a 304 SS substrate tested in a vacuum of 0.047 Pa (3.5×10^{-4} Torr). An 11.2N normal load was used (which matches the S_{max} value for the N₂ testing within 0.5%), and the test was run until failure. The average WS₂ particle size was 100 nm. The raw data are shown in blue, and a smoothed average of the data is shown in orange. The ordinate is in time units, and failure occurred at about 2800 cycles.

A summary of the vacuum tribometry results is shown in Table 2, along with previous data obtained in dry N_2 for those samples. The average friction values in the vacuum were similar to those for the N_2 testing, within the expected data uncertainty for these tests (as shown by the lengths of the error bars in Figure 12). In contrast, the endurance/cycle life for most of the coatings tested in the vacuum was markedly lower than for those tested in N_2 . This is not surprising, since it is well documented that wear lives of MoS_2 -based solid lubricants are higher in dry N_2 compared to vacuum [20,21]. MoS_2 wear particles form a third body that can act as a beneficial reservoir of lubricating material that is cycled back into the contact region. The N_2 is thought to be incorporated into MoS_2 wear particles—possibly as adsorbed molecules—influencing their plastic and shear properties as a third body so as to increase the wear life. WS_2 likely exhibits similar behavior, since WS_2 and MoS_2 have very similar crystallographic and electronic structures, as well as chemistry [1].

Table 2. Comparison of results from tribo-testing in a vacuum and dry N_2 . Vacuum testing was conducted at the Aerospace Corporation, and endurance and COF results were averaged between two tests. N_2 testing was conducted at Applied Tungstenite and represents single test results.

Coating	Endurance (Cycles) Dry N ₂ ^a	Avg. Endurance (Cycles) Vacuum	Steady-State COF Dry N ₂	Avg. Steady-State COF Vacuum
5 μm Ni + 80 wt% 15 μm MoS ₂ ^b	9000	920	0.023	0.037
1 μm Cu + 90 wt% 100 nm WS ₂	>10,000	2199	0.032	0.040
1 μm Cu + 80 wt% 24 μm WS ₂	>5000	3464	0.054	0.030
5 μm Ni + 91 wt% 15 μm MoS ₂	>5000	508	0.044	0.035
100 nm WS ₂ ^c	6300	2778	0.018	0.028
15 μm MoS ₂	6400	1324	0.025	0.036

^a Cycles at failure are listed, except for those with the ">" symbol, which indicates the test was stopped before failure at the indicated cycles. ^b Same sample as represented in Figure 9. ^c Same sample as represented in Figure 10.

3.2. Coating Characterization

Cross-sections of representative coatings were obtained using the FIB technique. The resultant cross-sections were then analyzed using SEM and EDX, enabling determination of the thickness of the coatings as well as the thickness variation (i.e., morphology) and distribution of elements within the coating.

Figure 16 shows an SEM image of a FIB cross-section of Cu/WS₂, cold sprayed from a feedstock mixture of 1 μ m Cu with 80 wt% of 24 μ m WS₂. The coating is within the two horizontal white lines on the image, between the lower darker region representing the substrate, and the upper lighter region representing a platinum film that was deposited to protect the surface during the FIB sectioning. Also shown in the figure are EDX false-color maps that each represent different elements, which enables facile visualization of the coating. Specifically seen are S from WS₂, W from WS₂, and Cu. The color intensity has been enhanced so that the Cu layer is seen clearly, even though XRF showed that it was only present in amounts of a few weight percent.



Figure 16. Scanning electron microscope (SEM) image of a focused ion beam (FIB) cross-section of a coating made from a nominal mixture of 1 μ m Cu with 80 wt% of 24 μ m WS₂ (**top**). The region within two horizontal white lines represents the area where energy-dispersive X-ray (EDX) maps were obtained (**middle**). Yellow represents S from WS₂, green is W from WS₂, and magenta is Cu. Also shown is a higher-magnification SEM image of the region in the blue oval in the top SEM image, showing the Cu-WS₂ coating (**bottom**).

The coating was shown to be thin, with an average thickness of $\leq 1 \mu m$. In addition, there was considerable thickness variation. However, based on the map resolution, it cannot be discerned if all areas of the substrate surface were covered with coating species. The surface analysis presented below will help in this regard.

The EDX maps indicated that the Cu appeared to be distributed in the same regions as the WS₂, without showing phase separation on the micron scale. This was surprising because the average size of the Cu particles used in the feedstock was 1 μ m, which is similar to the coating thickness. This can be explained by the fact that the Cu in the feedstock was present in a size distribution: the cold spray process apparently favored smaller particle sizes to be incorporated in the coating. This was even more striking for the WS₂, whose feedstock had a significantly larger average size (24 μ m) than the Cu, and much greater than the coating thickness. Here, again, smaller particles sizes were incorporated in the coating from the distribution, impacting the surface. For the WS₂, this may not be as dramatic as it seems, because the 24 μ m value refers to the width of the particles. Because of their anisotropic crystal structure, particles are generally formed in platelets with a much smaller thickness than width. As a result, films with a thickness much less than the particle width can form if the articles align with their long dimension oriented along the surface.

Using the EDX maps as a guide, the regions within the SEM images corresponding to the coating species could be identified. At the bottom of Figure 16, a higher-magnification SEM image is shown of the surface region obtained from the region in the top image located by a blue oval. The area representing the Cu-WS₂ coating in the cross-section appeared homogeneous, in agreement with the distribution seen in the EDX maps.

Figure 17 shows an SEM image of a FIB cross-section of a Cu/WS₂ coating that was cold sprayed from a feedstock mixture of 1 μ m Cu with 90 wt% 100 nm WS₂ (i.e., with a greater nominal amount of WS₂ than the coating shown in Figure 16, but with much smaller WS₂ particles). The EDX maps for this coating showed that it was qualitatively similar to the one in Figure 16, with thickness $\leq 1 \mu$ m, significant thickness variation, and homogeneous distribution of Cu with the WS₂. A higher-magnification SEM image is shown, which is located within the blue oval in the upper SEM image. Again, the coating material in this image appeared homogeneous, although with a few small inclusions on the right side of the material. These inclusions were not analyzed further, so it is not known if they are due to chemical variations or voids in the coating.

Figure 18 shows an SEM image of a FIB cross-section of an MoS₂ coating that was cold sprayed from a feedstock containing 15 μ m-diameter MoS₂ powder. The EDX maps for this coating showed that it was $\leq 1 \mu$ m in thickness, with greater thickness variation than the Cu/WS₂ coatings shown in Figures 16 and 17. In two higher-magnification SEM images, located within the blue ovals in the upper SEM image, regions of greater coating thickness are seen.

XPS spectra were acquired for several coatings to determine the elements present on the surface and their chemical state. In addition, the surface sensitivity of XPS helped in determining the coating coverage on the substrate surface. In Figure 19, an XPS wide scan of the surface of a coating made from a nominal mixture of 1 μ m Cu with 90 wt% 100 nm WS₂ is shown, and this coating was similar to the one represented in Figure 17. The spectrum showed the expected presence of the constituents of the coating, including Cu, W, and S. It also showed C and O that were from adsorbed contaminant species usually seen on the surface of air-exposed materials: the C is adventitious carbon, usually due to adsorbed organic species, while the O is from adsorbed H₂O and other oxygen-containing molecules, as well as oxidation products of the coating materials.



Figure 17. SEM image of a FIB cross-section of a coating made from a nominal mixture of 1 μ m Cu with 90 wt% 100 nm WS₂ (**top**). The region within the two horizontal white lines represents the area where EDX maps were obtained (**middle**). In the maps, yellow represents S from WS₂, green represents W from WS₂, and magenta represents Cu. Also shown is a higher-magnification SEM image of the region shown in the blue oval in the top SEM image, showing the Cu-WS₂ coating (**bottom**).



Figure 18. SEM image of a FIB cross-section of a coating made from a 15 μ m-diameter MoS₂ powder (**top**). The region within the two horizontal white lines represents the area where EDX maps were obtained (**middle**). In the maps, yellow represents S from MoS₂ and red represents Mo from MoS₂. Also shown are two higher-magnification SEM images of the regions shown in the blue ovals in the top SEM image, showing the MoS₂ coating (**bottom**).

The Cu content (as a percent of the coating constituents Cu, W, and S) was 27 at%, which is equivalent to 22 wt%. This is significantly higher than the bulk value of ~1 wt% that was calculated by XRF. The mean escape depth (MED) calculated for the Versaprobe XPS instrument setup for Cu was 0.7 nm [22], whereas XRF probed the entire thickness of the coating. As such, Cu appeared to be significantly enhanced at the surface of the coating.

In the cold spray technique, the temperature of the powder-laden gas jet and the temperature of the powder material were low enough to prevent a phase change or stress in the deposit or substrate. As such, the surface enhancement of Cu was likely not due

to chemical reaction of Cu with WS₂ or the steel substrate. Therefore, either Cu particles coated the surface of WS₂ particles before they adhered to the surface to form a coating, or Cu particles adhered to the surface of the coating after WS₂ particles were deposited. Either possibility is not expected to significantly affect the performance of the coating in terms of cycle life or steady-state COF. Because the COF of Cu was higher than that for WS₂, the initial COF (i.e., in the first few cycles) may be increased. However, this was also likely an insignificant effect because initial/pre-run-in COF is higher for most solid lubricating materials anyway.

A small Fe peak was seen on the edge of a Cu Auger transition, whose intensity indicated that Fe only comprised ~3% of the detected surface species. The Fe was detected from the 304 SS substrate. As such, most of the surface was covered by the solid lubricant coating, at least to a thickness of 2–3 nm, i.e., several times the MED for the Fe XPS peak. This helped to further describe the coating morphology: SEM with associated EDX maps of a similar coating implied significant thickness variation (see Figure 17), but the XPS showed that even in the thin regions, sufficient solid lubricant coating was present to provide low friction.



Figure 19. XPS wide scan of the surface of a coating made from a nominal mixture of 1 μ m Cu with 90% 100 nm WS₂, similar to the coating shown in Figure 17. Primary photoelectron peaks of the detected species are labeled.

A high-resolution XPS scan of the surface of the Cu/90% WS₂ coating taken in the W 4f region is shown in Figure 20. The spectrum is representative of mostly WS₂ with a small amount of WO₃. A thin, oxidized surface film is typical of metal sulfide powders and coatings due to exposure to humid air in the atmosphere [23]. A high-resolution XPS scan in the S 2p region is shown in Figure 21. The spectrum is representative of predominantly WS₂ with a small amount of sulfate species. Such a sulfate species is consistent with the observation of oxidized W because sulfuric acid is a product of the metal sulfide oxidation reaction [23].



Figure 20. High-resolution XPS scan of the surface of a coating made from a nominal mixture of 1 μ m Cu with 90% 100 nm WS₂ (same coating as in Figure 19). The scan is of the W 4f region. Typical of metal sulfide coatings, a small amount of the WS₂ at the surface of the coating oxidized to WO₃.



Figure 21. High-resolution XPS scan of the surface of a coating made from a nominal mixture of 1 μ m Cu with 90% 100 nm WS₂ (same coating as in Figure 19). The scan is of the S 2p region. A small amount of sulfate is seen in the spectra, which is expected as an oxidation product of WS₂ in addition to WO₃.

An XPS wide scan of the surface of a coating made from a nominal mixture of 5 μ m Ni with 80 wt% 15 μ m MoS₂ is shown in Figure 22 (the same coating whose friction scan is

seen in Figure 9). As expected, Mo and S from MoS_2 were apparent in the spectrum, with only a small peak for Ni (less than 1 wt%). Based on FIB/SEM/EDX results, the bulk Ni content was estimated to be ~1 wt% (XRF could not be used because of the high Ni content in the 304 SS substrate). As such, there was no apparent surface enhancement of the Ni, unlike that for the Cu-containing coating, as discussed above.

Similar to the wide scan for the Cu/90% WS₂ coating in Figure 19, the Ni/80% MoS₂ coating showed a small Fe peak that originated from the 304 SS substrate. As before, Fe only comprised ~3% of the detected surface species. As such, most of the surface was covered by the solid lubricant coating, at least to a thickness of 2–3 nm, i.e., several times the MED for the Fe XPS peak. Again, although we expected significant thickness variation in this coating, XPS showed that even in the thin regions, sufficient solid lubricant coating was present to provide low friction.

A high-resolution XPS scan of the surface of the Ni/80% MoS₂ coating taken in the Mo 3d region is shown in Figure 23. Similar to the corresponding W 4f spectrum for the Cu/90% WS₂ coating in Figure 20, it is representative of mostly metal sulfide (MoS₂), with a small amount of metal oxide (MoO₃). A high-resolution XPS scan in the S 2p region is shown in Figure 24. Similar to that for the corresponding S 2p spectrum for the Cu/90% WS₂ in Figure 21, the spectrum is representative of mostly metal sulfide (MoS₂), with a small amount of a sulfate species.



Figure 22. XPS wide scan of the surface of a coating made from a nominal mixture of 5 μ m Ni with 80% 15 μ m MoS₂. Primary photoelectron peaks of the detected species are labeled.



Figure 23. High-resolution XPS scan of the surface of a coating made from a nominal mixture of 5 μ m Ni with 80% 15 μ m MoS₂ (same coating as in Figure 22). The scan is of the Mo 3d region. Typical of metal sulfide coatings, a small amount of MoS₂ at the surface of the coating oxidized to MoO₃. The S 2s peak appeared at ~226.5 eV.



Figure 24. High-resolution XPS scan of the surface of a coating made from a nominal mixture of 5 μ m Ni with 80% 15 μ m MoS₂ (same coating as in Figure 22). The scan is of the S 2p region. A small amount of sulfate was seen in the spectra, which was expected as an oxidation product of MoS₂, in addition to MoO₃.

An XPS wide scan of the surface of a coating made from pure 15 μ m MoS₂ feedstock is shown in Figure 25, which is the same coating whose SEM and cross-section EDX map in

Figure 18 showed significant thickness variation. The XPS scan showed an even smaller Fe peak than that for the Ni/MoS₂ coating in Figure 22, here comprising only ~1% of the detected surface species. As such, virtually all of the surface was covered by solid lubricant to a thickness of at least 2–3 nm, which explains its good tribological performance, even from the first few cycles of testing (see Figure 11 for a friction scan of a similar pure MoS₂ coating).



Figure 25. XPS wide scan of the surface of a coating made from 15 μ m MoS₂. Primary photoelectron peaks of the detected species are labeled.

4. Discussion of Potential Applications of Cold Spray Solid Lubricant Coatings

Based solely on friction and wear performance, the various types of cold spray solid lubricant coatings we developed behaved similarly, with small differences in cycle life: the Cu-containing WS₂ and MoS₂ coatings and the Ni/WS₂ coatings exhibited modestly higher cycle lives. The pure WS₂ and MoS₂ coatings exhibited slightly lower cycle lives, but they may be desirable based on the materials' compatibility: the amounts of Cu and Ni in the metal-containing cold spray coatings may be minimal (a few percent); however, the use of these metals may still be precluded in some applications.

 MoS_2 is generally superior tribologically to WS_2 at ambient temperature in inert and vacuum environments [24,25], but this study did not support that for cold spray coatings fabricated using the KM technique. The choice between WS_2 - and MoS_2 -containing coatings may be based on their performance at varying temperatures. In a vacuum, WS_2 decomposes at only a slightly lower temperature than MoS_2 (1040 and 1090 °C, respectively) [26]. However, for static exposure in air, WS_2 is more stable at elevated temperatures: the threshold appears to be 390 °C, below which MoS_2 oxidizes more slowly, and above which WS_2 oxidizes more slowly [27]. For ball-on-flat testing of MoS_2 and WS_2 powders in air, the friction of MoS_2 began increasing above ~510 °C, while that for WS_2 began increasing above ~690 °C [28].

There are several types of metal-disulfide-based solid lubricant coatings in use in spacecraft, including mainly bonded, sputtered, and impinged coatings (these are compared in detail in [1]). There are a few compositions from several vendors available for sputtered MoS₂-based coatings, and there are literally hundreds if not thousands of bonded MoS₂

coatings available from scores of vendors, and both WS_2 and MoS_2 impinged coatings can be purchased from several vendors (see [29,30] for research on impinged MoS_2 coatings). The question may arise, do we need another method for fabricating solid lubricant coatings? The answer is related to the understanding that there are no panaceas in this field: no coating formulation is ideal for all applications. There are tradeoffs between coatings based on such attributes as coating thickness, friction, cycle life, and even cost.

Table 3 presents the various attributes of the predominant coating techniques, including the newly developed cold spray method. It shows that there are specific application niches for each method. Impinged coatings are generally appropriate only for very low cycle applications. Bonded coatings are the mainstay of spacecraft, being used for many sliding applications, such as latches, release mechanisms, fasteners, actuators, and even for gears that are used at lower loads. But they cannot be used for some precision ball bearings because of their higher thickness and limited load-carrying ability. Sputter-deposited coatings are ideal for such precision applications because of their low thickness, good load-carrying ability, and significant cycle life, especially in rolling applications. However, they are the most expensive coating type in the commercially available solid lubricant coating family.

Table 3. Attributes and performance of principal cold spray metal disulfide solid lubricant coatings compared to other metal disulfide solid lubricant coating fabrication techniques ^a.

Attributes	Impinged Coatings	Cold Spray Coatings	Resin- or Inorganic-Bonded Coatings	Sputtered Coatings
Friction	Very low	Very low	Very low	Super low
Cycle life	Low	Moderate	High	High
Cycle life variability	High	Moderate	Moderate	Moderate
Mean Hertzian contact stress limit (S _m , GPa)	1.4	1.4	Resin: 0.4 Inorganic: 1.0	1.4
Thickness	\leq 0.1 μ m	$\leq 1 \mu m$	8–18 μm	$\leq 1 \mu m$
Storage stability in air environments	Fair to good	Fair to good	Resin: good Inorganic: poor	Poor to fair, depends on composition
LOX compatibility	Good	Good	Resin: poor Inorganic: good	Good
Fabrication throughput	High	High	Moderate	Low
Cost	Very low	Low	Low	High
Summary of optimum applications	Low cycle dimension-critical mechanisms for low cost	Precision-/dimension- critical applications, e.g., ball bearings for low cost	Sliding mechanisms with requirements for higher cycles with lower loads and precision	Precision-/dimension- critical applications, e.g., ball bearings with high cycles at higher cost

^a Attributes of impinged, bonded, and sputtered coatings used on spacecraft mechanisms were obtained primarily from [1].

There is clearly a niche for cold spray solid lubricant coatings. They demonstrated a significantly longer life and reliability than the impinged coatings, and significantly lower thickness than bonded coatings. Although some sputtered coatings have demonstrated significantly higher cycle lives, the cold spray coatings may be appropriate for many precision ball-bearing applications. Solid lubricated bearings are recommended to be used with both self-lubricating cages and coatings for the races. The main purpose of the coating is to provide low friction and wear protection during the run-in phase, as solid lubricant material is slowly transferred from the cage to the ball surface, and then to the race surfaces to provide steady-state lubrication. In addition, our results have only evaluated pure

sliding in high contact stress conditions: in rolling applications, such as ball bearings, the coating cycle life may be significantly higher.

Although sputtered coatings may be preferred in some applications due to high cycle requirements, the cold spray coatings have comparative advantages. The cost of the cold spray coatings is expected to be significantly lower: a cold spray coating can be deposited in about one minute in an air environment, even on complex surfaces, while deposition of sputtered coatings may take hours and must be applied in a plasma within a high vacuum chamber. In addition, the sensitivity of sputtered MoS₂-based coatings to storage in humid atmospheres is an issue and has been shown to vary with the specific coating composition [23]. Cold spray coatings are based on micron-sized particles, such as bonded and impinged coatings, and they would be expected to exhibit improved storage stability compared to sputtered coatings.

5. Summary

This study presented a new class of solid lubricant coatings that are based on the cold spray technique, using solid lubricant powders of the metal disulfides WS₂ or MoS₂, either pure or mixed with powdered metals, such as Cu and Ni. Friction and wear results were obtained using ball-on-flat reciprocating tribometry of coated 304 SS flats used with uncoated 100Cr6 steel balls. Coating thickness, morphology, and composition were analyzed using XRF spectrometry and studying FIB-produced cross-sections with SEM and EDX analysis. Specific findings follow:

- By increasing the metal disulfide:metal ratio and optimizing cold spray equipment parameters, coatings can be grown that exhibit much lower friction (COF values of 0.03 ± 0.01) and thickness ($\leq 1 \mu m$) than previous metal/metal disulfide cold spray coatings. Performance was demonstrated in both dry nitrogen and vacuum environments in sliding conditions at high Hertzian contact stresses (i.e., for S_{max} values up to 1386 MPa (201 ksi)) to achieve failure in a reasonable timeframe.
- Cu-containing metal disulfide coatings exhibited higher cycle lives than the pure metal disulfide coatings, even though the Cu content was only ~1 wt%.
- Cross-sectional analysis of the coatings showed significant thickness variation, although surface analysis using XPS showed that the substrates were virtually covered by solid lubricating material. EDX mapping of cross-sections showed that particle sizes in the coatings were considerably smaller than the average particle size in the initial feedstock, suggesting that the process favored the incorporation of smaller particles into the coating.
- Analysis of wear track profiles for coatings that were run to 3000 cycles (i.e., pre-failure) yielded specific wear rates in the range 3–7 × 10⁻⁶ mm³N⁻¹m⁻¹, which is typical for solid lubricant coatings.
- No wear was apparent on the surfaces of 100Cr6 steel ball counter-faces.
- When compared to other coating techniques, such as impingement, bonded coatings, and sputter deposition, the cold spray method represents a niche that has heretofore been vacant. For example, it may be useful for many precision ball-bearing applications, since cold spray can yield higher throughput and lower costs than sputtered coatings. In addition, because cold spray is a particle-based technology, it may exhibit improved storage stability compared to sputtered coatings.

Author Contributions: Conceptualization, J.R.L., P.W. and E.W.; methodology, J.R.L., P.W. and E.W.; validation, J.R.L. and P.W.; formal analysis, J.R.L.; investigation, J.R.L., P.W., W.H.M., A.J.C. and S.D.S.; resources, P.W.; data curation, J.R.L. and P.W.; writing—original draft preparation, J.R.L.; writing—review and editing, J.R.L., P.W., E.W., W.H.M., A.J.C. and S.D.S.; visualization, J.R.L.; supervision, P.W. and E.W.; project administration, J.R.L. and P.W.; funding acquisition, P.W. and E.W. All authors have read and agreed to the published version of the manuscript.

Funding: This research was funded by NASA under Small Business Innovative Research (SBIR) Contract No. 80NSSC21C0529.

Data Availability Statement: The original contributions presented in the study are included in the article, further inquiries can be directed to the corresponding author/s.

Acknowledgments: The authors gratefully acknowledge the support of Merilee Woods during this project.

Conflicts of Interest: Jeffrey R. Lince is employed by Space Tribology Consulting, Inc. Peter Woods and Eric Woods are employed by Applied Tungstenite, Inc. Wai H. Mak, Andrew J. Clough and Scott D. Sitzman are employed by The Aerospace Corporation. The funding agency had no role in the design of the study; in the collection, analyses, or interpretation of data; in the writing of the manuscript, or in the decision to publish the results.

References

- 1. Lince, J.R. Effective application of solid lubricants in spacecraft mechanisms. Lubricants 2020, 8, 74. [CrossRef]
- 2. Papyrin, A. The development of the cold spray process. In *The Cold Spray Materials Deposition Process: Fundamentals and Applications*, 1st ed.; Champagne, V.K., Ed.; Woodhead: Cambridge, UK, 2007.
- 3. Botef, I.; Villafuerte, J. Overview. In *Modern Cold Spray: Materials, Process, and Applications*; Villafuerte, J., Ed.; Springer: New York, NY, USA, 2015; Chapter 1. [CrossRef]
- Yamada, M.; Wakabayashi, J.; Fukumoto, M.; Kitamura, J. Fabrication of Cu-MoS₂ composite coating by cold spraying and evaluation of its property. In Proceedings of the ITSC 2009: International Thermal Spray Conference, Las Vegas, NV, USA, 4–7 May 2009. [CrossRef]
- 5. Aggarwal, G. Development of Self-Lubricating Coatings via Cold Spray Process: Feedstock Formulation and Deformation Modeling. Ph.D. Thesis, The Pennsylvania State University, University Park, PA, USA, 2007.
- Smid, I.; Segall, A.E.; Walia, P.; Aggarwal, G.; Eden, T.J.; Potter, J.K. Cold-sprayed Ni-hBN self-lubricating coatings. *Tribol. Trans.* 2012, 55, 599. [CrossRef]
- Zhang, Y.; Shockley, J.M.; Vo, P.; Chromik, R.R. Tribological behavior of a cold-sprayed Cu–MoS₂ composite coating during dry sliding wear. *Tribol. Lett.* 2016, 62, 1. [CrossRef]
- 8. Zhang, Y.; Descartes, S.; Vo, P.; Chromik, R.R. Cold-sprayed Cu-MoS₂ and its fretting wear behavior. *J. Therm. Spray Technol.* **2016**, 25, 473. [CrossRef]
- 9. Zhang, Y.; Epshteyn, Y.; Chromik, R.R. Dry sliding wear behaviour of cold-sprayed Cu-MoS₂ and Cu-MoS₂-WC composite coatings: The influence of WC. *Tribol. Int.* **2018**, *123*, 296. [CrossRef]
- 10. Radhakrishnan, J.; Radhika, N.; Vighneshwar, R. Enhancement of tribological properties of pure copper through cold sprayed MoS₂ coating. *Mater. Res. Express.* **2019**, *6*, 096448. [CrossRef]
- 11. Dey, D.; Sarkar, S.; Mahata, A.; Choudhury, A.R.; Nath, A.K. Microstructural and tribological properties of high-performance Inconel 625 alloy-WS₂ self-lubricious composite coating by laser assisted cold spray. *J. Alloys Compd.* **2024**, *983*, 173840. [CrossRef]
- 12. Tapphorn, R.; Gabel, H. Brush-Sieve Powder-Fluidizing Apparatus for Feeding Nano-Size and Ultra-Fine Powders. U.S. Patent 7,273,075 B2, 25 September 2007.
- 13. Buttery, M.; Lewis, S.; Kent, A.; Bingley, R.; Cropper, M. Long-Term Storage Considerations for Spacecraft Lubricants. *Lubricants* 2020, *8*, 32. [CrossRef]
- 14. Singer, I.L.; Bolster, R.N.; Wegand, J.; Fayeulle, S.; Stupp, B.C. Hertzian stress contribution to low friction behavior of thin MoS₂ coatings. *Appl. Phys. Lett.* **1990**, *57*, 995. [CrossRef]
- 15. Amontons, G. Memoires de l'Academie Royale des Sciences; Chez Gerard Kyuper: Amsterdam, The Netherlands, 1706; pp. 257–282.
- 16. Archard, J.F. Wear theory and mechanisms. In *Wear Control Handbook*; Peterson, M.B., Winer, W.O., Eds.; ASME: New York, NY, USA, 1980.
- 17. ASTM Standard G133-05; Standard Test Method for Linearly Reciprocating Ball-on-Flat Sliding Wear. ASTM International: West Conshohocken, PA, USA, 2016. Available online: www.astm.org (accessed on 6 February 2019). [CrossRef]
- 18. Scharf, T.W.; Prasad, S.V. Solid lubricants: A review. J. Mater. Sci. 2013, 48, 511. [CrossRef]
- 19. Wear. Available online: https://en.wikipedia.org/wiki/Wear (accessed on 27 May 2024).
- 20. Gardos, M.N. Anomalous Wear Behaviour of MoS₂ Films in Moderate and Dry Nitrogen. Tribol. Lett. 1995, 1, 67-85. [CrossRef]
- 21. Colas, G.; Saulot, A.; Bouscharain, N.; Godeau, C.; Michel, Y.; Berthier, Y. How far does contamination help dry lubrication efficiency? *Tribol. Int.* 2013, 65, 177. [CrossRef]
- 22. Powell, C.J.; Jablonski, A. *NIST Electron Effective-Attenuation-Length Database–Version 1.3*; National Institute of Standards and Technology: Gaithersburg, MD, USA, 2011.
- Lince, J.R.; Loewenthal, S.H.; Clark, C.S. Tribological and Chemical Effects of Long Term Humid Air Exposure on Sputter-Deposited Nanocomposite MoS₂ Coatings. Wear 2019, 432, 202935. [CrossRef]
- Anderson, M.J.; Cropper, M.; Roberts, E.W. The Tribological Characteristics of Dicronite. In Proceedings of the European Space Mechanisms and Tribology Symposium (ESMATS), Liverpool, UK, 19–21 September 2007. Available online: https: //esmats.eu/esmatspapers/pastpapers/pdfs/2007/anderson.pdf (accessed on 25 April 2024).

- Jansson, M.; Koenen, J.; Viviente, J.-L.; Tvaruzka, A.; Merstallinger, A. Development of Dry Lubricated Harmonic Drives for Space Applications ("harmLES"). In Proceedings of the 15th European Space Mechanisms and Tribology Symposium (ESMATS 2013), Noordwijk, The Netherlands, 25–27 September 2013. Available online: https://esmats.eu/esmatspapers/pastpapers/ pdfs/2013/jansson.pdf (accessed on 25 April 2024).
- Brainard, W.A. The Thermal Stability and Friction of the Disulfides, Diselenides, and Ditellurides of Molybdenum and Tungsten in Vacuum (10⁻⁹ to 10⁻⁶ Torr); NASA Technical Note, NASA TN D-5141; National Aeronautics and Space Administration: Washington, DC, USA, 1969.
- 27. Winer, W.O. Molybdenum disulfide as a lubricant: A review of the fundamental knowledge. Wear 1967, 10, 422. [CrossRef]
- 28. Higgs, C.F., III; Heshmat, C.A.; Heshmat, H. Comparative Evaluation of MoS₂ and WS₂ as Powder Lubricants in High Speed, Multi-Pad Journal Bearings. *J. Tribol.* **1999**, *121*, 625. [CrossRef]
- 29. Scharf, T.W.; Diercks, D.R.; Gorman, B.P.; Prasad, S.V.; Dugger, M.T. Atomic Layer Deposition of Tungsten Disulphide Solid Lubricant Nanocomposite Coatings on Rolling Element Bearings. *Tribol. Trans.* **2009**, *52*, 284–292. [CrossRef]
- Curry, J.F.; Argibay, N.; Babuska, T.; Nation, B.; Martini, A.; Strandwitz, N.C.; Dugger, M.T.; Krick, B.A. Highly Oriented MoS₂ Coatings: Tribology and Environmental Stability. *Tribol. Lett.* 2016, 64, 11. [CrossRef]

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.